

Bute Fabrics Ltd
4 Barone Road
Rothesay
Isle of Bute
Scotland
PA20 0DP
United Kingdom

Attention: Catherine Murray

BTX 27617(1)/PS/04

Page 1 of 2

Date: 27 August 2004

REPORT ON SUBMITTED SAMPLE RECEIVED ON 29 July 2004

Sample Description: Fabric ref DS4496/0101 (CF751)

Details of sample: Test Ref: 2593

Test(s) requested: BS 5852:1990

Test results:

Date(s) of test Tested between 28/07/04 and 27/08/04

Flammability in accordance with BS5852: 1990

The sample was tested after water soaking in accordance with BS5651: 1989 clause 3 for Ignition source 5 and after water soaking procedure as specified in BS EN 1021-1:1994 for Ignition sources 0 & 1

Filling material used : An combustion modified foam in-fill of approximate density 35 kg/cu. m

The following test results relate only to the ignitability of the combination of upholstery composites (section 4 of BS5852: 1990) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Ignition Source 0 (Smouldering cigarette) (BSEN1021-1: 1994)


	Test 1	Test 2	Result
No flaming, smoking or progressive smouldering was observed within 60 minutes of the placement of the cigarettes. (Pass)	Pass	Pass	PASS

Ignition Source No.1 (match-equivalent butane flame) (BSEN1021-2: 1994)

15 second flame application time

	Test 1	Test 2	Result
Flaming ceased within two minutes of the removal of the ignition source and no progressive smouldering was observed within 60 minutes of the removal of the ignition source. (Pass)	Pass	Pass	PASS

All orders are accepted and all services are rendered subject to the General Conditions of Service available upon request and accessible at www.sgs.com.
Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein.



Ignition Source No.5 (Wood crib) (BS5852 : 1990)

	Test 1	Test 2	Result
All flaming, and smoking ceased within 10 minutes of the ignition of the crib and no progressive smouldering was observed 60 minutes after the ignition of the crib. (Pass)	Pass	Pass	PASS

Comments: The composite tested complies with the requirements of BS 5852:1990 in respect of ignition sources 0, 1 and 5.

Paula Smith
Textile Technologist
Softlines Department

Mark Dawes B.Sc. (Hons), C. Text, ATI
Senior Textile Technologist
Softlines Department