



Textiles and Apparel Solutions Centre,
 The Warehouse, Brewery Lane,
 Leigh, Lancashire, WN7 2RJ, UK
 Telephone: +44 (0) 1942 265700
 Facsimile: +44 (0) 1942 670 788
 www.intertek.com/consumergoods

BS EN 14465:2003 Test Report

Report Ref: LEHTX00936530	Buying Division: NONE GIVEN
Date Received: 06/02/2017	Date Issued: 09/02/2017

Company Name & Address	BUTE FABRICS LTD 4 BARONE ROAD ROTHESAY ISLE OF BUTE
Contact Name	PA20 ODP M A BAXTER

Order No.:	NONE GIVEN
Description:	WOVEN FABRIC
Colour(s):	OPAL
Supplier:	BUTE FABRICS LTD
End Use:	CURTAIN / UPHOLSTERY
Quoted Composition:	100% PURE NEW WOOL
Ref/Style/Stroke No.:	COAST CF944
Quality:	coast cf944
Batch No.:	NONE GIVEN
Spec. No.:	TABLE 1

Test	Method	Colour	Pass/Fail
COLOUR FASTNESS TO LIGHT - STD 5	BS EN ISO 105 B02: 2014		See Notes
ABRASION RESISTANCE (FLAT WOVEN)	BS EN ISO 12947-2/BS EN 14465: 2003 ANNEX A		Pass B
PILLING	BS EN ISO 12945-1:2001		Pass

The colour fastness to light result will be forwarded once the test is complete

The flammability result will be forwarded once the test is complete on report no.936532

Janet Waterworth
 (Specification Coordinator)





Textiles and Apparel Solutions Centre,
The Warehouse, Brewery Lane,
Leigh, Lancashire, WN7 2RJ, UK
Telephone: +44 (0) 1942 265700
Facsimile: +44 (0) 1942 670 788
www.intertek.com/consumergoods

Upholstery - Colour Fastness to Light (STD 5)					
Sample	Results				Minimum Requirements
	Results to follow				Grade 5
Overall Performance Level					
BS 2543: 2004 Classification (Minimum levels for customer reference)					
	LD	GD	HD	GC	SC
All Fabrics	B - 5	B - 5	B - 5	B - 5	N/A



Upholstery - Martindale Abrasion (12 kPa Load)		RH 65% +/-4% / Temp 20°C +/-2°C			
Sample	Results				Minimum Requirements
	Change in Shade @ 3,000 Revs = Grade 4-5				A=35,000 B=12,000-30,000 C=4,000-10,000
Fabric Type	Heads 2,4 No fabric breakdown @ 30,000 revs Fabric breakdown @ 35,000 revs				
Flat Woven	Heads 3 No fabric breakdown @ 35,000 revs Fabric breakdown @ 40,000 revs				
Overall Result	30,000				
Overall Performance Level	B				
BS 2543: 2004 Classification (Minimum levels for customer reference)					
	LD	GD	HD	GC	SC
Flat Woven	B - 15,000	B - 20,000	B - 25,000	B - 30,000	A - 40,000
Figured Weaves	B - 12,000	B - 15,000	B - 20,000	B - 30,000	A - 40,000
Woven/Flocked/Non-Woven Pile Fabrics	C - 15,000	C - 20,000	B - 25,000	B - 25,000	B - 30,000
Knitted	B - 15,000	B - 20,000	B - 25,000	B - 25,000	B - 30,000



Textiles and Apparel Solutions Centre,
The Warehouse, Brewery Lane,
Leigh, Lancashire, WN7 2RJ, UK
Telephone: +44 (0) 1942 265700
Facsimile: +44 (0) 1942 670 788
www.intertek.com/consumergoods

Pilling Resistance - Pillbox Method		RH 65% +/-2% / Temp 20°C +/-2°C
Sample	Results	Requirements
As Received	<p>Total Revs : 36,000</p> <p>Pilling after laundering - Grade N/A</p> <p>Pilling after test - Grade Grade 4 Fuzzing</p>	36,000 revs





Textiles and Apparel Solutions Centre,
The Warehouse, Brewery Lane,
Leigh, Lancashire, WN7 2RJ, UK
Telephone: +44 (0) 1942 265700
Facsimile: +44 (0) 1942 670 788
www.intertek.com/consumergoods

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

